

TEROSON® PU 9225

October 2017

Product description

TEROSON® PU 9225 provides the following product characteristics:

Technology	Polyurethane
Product type	For the repair of plastic parts
Additional information	2-Component

TEROSON® PU 9225 is a polyurethane based two-component adhesive which cures at room temperature. For accelerated curing it is recommended to increase the temperature up to 60 to 70 °C. The product is supplied in a convenient twin cartridge. TEROSON® PU 9225 can be painted with standard commercial car repair refinishing paints. When applying TEROSON® PU 9225 to plastics the use of an approved Henkel primer is absolutely necessary. Detailed information see directions of use.

Application areas

TEROSON® PU 9225 is used for repair of bumpers, trim and body parts made of plastic e.g. PP / EPDM, SMC, PC, PA, ABS, and PUR.

Technical data

(Typical test results)

Component A

Colour	yellow
Density	~1.4 g/cm³
Solids	>98%

Component B

Colour	black
Density	~1.7 g/cm³
Solids	>98%
Mixing Ratio A:B, by volume	1 : 1

Mixture (Component A + B)

Colour	dark grey
Potlife (23°C)	~10 min(s).
Tack-free time (23 °C, 50% rh)	~30 min(s).
Curing time at 23 °C	~5 hr(s).
Layer thickness	3 mm
Solid to hand pressure	
at 23 °C	~2 hr(s).
at 80 °C	~30 min(s).
Shore A hardness	~90
	5 hr(s). at 23 °C
Grindability	15 min(s). at 60 to 70 °C
Shear strength	
After 2 d (23 °C, 50 % rh)	13 MPa
Layer thickness	0.3 mm
Cross head speed	10 mm/min.
Paintability	good
Application temperature	15 to 30°C
In service temperature	-40 to 80°C

Preliminary statement

Prior to use it is necessary to read the **Safety Data Sheet** for information about precautionary measures and safety recommendations. Also, for chemical products exempt from compulsory labeling, the relevant precautions should always be observed. Please also refer to the local safety instructions and contact Henkel for analytical support.

Application

Insert the cartridge into a suitable application gun. Apply pressure to the cartridge(s) to ensure a simultaneous and homogeneous flow of both components. Thereafter, attach the static mixer and cut the tip to provide for the desired bead size. Discard the first 2 cm of extruded adhesive bead. TEROSON PU 9225 is applied directly to the substrates. Any excess material should be removed immediately after application. If material is left in the cartridge leave the static mixer attached. For further use of the product, simply remove the mixer and install a new one. In case of plastic repair the use of woven fiberglass mat is recommended for reinforcing,

Curing

Curing occurs at room temperature. To get a faster grindability the parts bonded with TEROSON® PU 9225 can be warmed up to 60 to 70 °C for minimum 15 minutes.



Reinforcing

In case of simple cracks TEROSON® PU 9225 can be applied in one step to rear and front side. For more difficult damages, the adhesive should be applied to both sides separately. Start with two continuous beads on the rear side and place them to both sides of the damaged area (bond with minimum 100 mm). For large damages e.g. holes, it is recommended to reinforce the complete damaged area with woven fibre glass mat by incorporating the mat in the beads. Reinforce initial crack areas with woven glass fibre mat in the same way. Then apply TEROSON® PU 9225 on top of the reinforced matting and smooth the surface. Ensure that the adhesive is pressed through the crack and the fibre glass mat to the front side to guarantee a reliable bonding. During applying TEROSON® PU 9225, keep the mixer tip within the material to avoid air inclusions. Apply an excess of TEROSON® PU 9225 in the same way to the front side.

Pretreatment for finish

After curing of the material these following steps are necessary: Sanding and cleaning and pretreating (P150/ P240, TEROSON® VR 20; priming (TEROSON® 150); further treatment e.g. filling, painting has to be carried out according to paint manufacturers directions for painting plastics.

Cleaning

1. Freshly applied and uncured material should be removed with a dry cloth and then cleaned off with a suitable solvent.
2. Cured adhesive can only be removed with a machine.

Storage

Frost sensitive	no
Recommended storage temperature, °C	10 to 25

Classification

Please refer to the corresponding **Safety Data Sheet** for details on:

Hazardous Information

Transport Regulations

Regulatory information

Disclaimer

The information provided in this Technical data sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product. Any liability in respect of the information in the Technical data sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product. Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Corporation, or Henkel Canada Corporation, the following disclaimer is applicable:

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

Reference 1