

MOLYKOTE® METAL PROTECTOR PLUS WAX SOLUTION

Corrosion protection coating

FEATURES

- ◆ Long-term corrosion protection
- ◆ Transparent coating
- ◆ Low coefficient of friction

COMPOSITION

- ◆ Synthetic wax
- ◆ Corrosion inhibitor
- ◆ Solvent
- ◆ Contains white spirit

APPLICATION

- ◆ Corrosion protection for metal parts which have to be stored or transported.

TYPICAL PROPERTIES

Specifications writers: These values are not intended for use in preparing specifications. Please contact Dow Corning GmbH, Wiesbaden, Germany before writing specifications on this product.

Standard*	Test	Units	Result
	Colour		
	Density		
ISO 2811	Density at 20°C	g/ml	0.84
	Flash point	°C	28
	Coefficient of friction		
	Press-Fit test $\mu =$		0.12
	Corrosion protection		
ISO/R 1456	Salt spray test	h	510

* ISO: International Standardisation Organisation

HOW TO USE

How to apply

Apply to cleaned surfaces by dipping, spraying or painting. Drying time at room temperature approx. 90 minutes. Several coats can be applied to enhance corrosion protection (letting them dry in between). Thinner coatings can be achieved by diluting with white spirit. By virtue of the compatibility of MOLYKOTE Metal Protector Plus with common lubricants, there is usually no need to wash off the film before using the devices/equipment. Should this be necessary, it can be done with white spirit. After use, clean spray can valves by spraying inverted.

HANDLING PRECAUTIONS

Avoid contact with the eyes.

A Product Safety Data Sheet should be obtained from your nearest Dow Corning sales office prior to use.

ATTENTION: Before handling, read product information, Product Safety Data Sheets and container labels for safe use, and any physical and/or health hazard information.

USABLE LIFE AND STORAGE

When stored at or below 20°C in the original unopened containers this product has a usable life of 60 months from the date of production.

Dow Corning will guarantee the usable life of this product until the date indicated on the packaging. This date is shown by the letters "EXP" (meaning Expiry) followed by 4 digits, which stand for the month (last day) and year. Example: "EXP 03/99" means use by 31 March 1999.

PACKAGING INFORMATION

This product is available in different standard container sizes. Detailed container size information should be obtained from your nearest

Dow Corning sales office or
Dow Corning distributor.

LIMITATIONS

This product is neither tested nor
represented as suitable for medical or
pharmaceutical uses.

HEALTH AND ENVIRONMENTAL INFORMATION

Dow Corning's Health, Environment
and Regulatory Affairs (HERA)
Department is available to support
customers for their product safety
needs. For further information, you
can contact this group at:

Dow Corning Europe
HERA Department
Rue Général de Gaulle, 62
B-1310 La Hulpe
Belgium
TEL:
Int +32 (0)2 655 2523
Int +32 (0)2 655 2304
FAX:
Int +32 (0)2 655 2013

The information contained herein is offered in good faith based on Dow Corning's research and is believed to be accurate. However, because conditions and methods of use of our products are beyond our control, this information shall not be used in substitution for customer's tests to ensure that Dow Corning's products are fully satisfactory for your specific applications. Dow Corning's sole warranty is that the product will meet its current sales specifications. Your exclusive remedy for breach of such warranty is limited to refund of purchase price or replacement of any product shown to be other than as warranted. DOW CORNING SPECIFICALLY DISCLAIMS ANY OTHER EXPRESS OR IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR MERCHANTABILITY. UNLESS DOW CORNING PROVIDES YOU WITH A SPECIFIC, DULY SIGNED ENDORSEMENT OF FITNESS FOR USE, DOW CORNING DISCLAIMS LIABILITY FOR ANY INCIDENTAL OR CONSEQUENTIAL DAMAGES. SUGGESTIONS OF USE SHALL NOT BE TAKEN AS INDUCEMENTS TO INFRINGE ANY PATENT.

**UNITED KINGDOM, NORDIC COUNTRIES,
BENELUX, SOUTH AFRICA, EIRE & MIDDLE EAST**
Dow Corning
UNITED KINGDOM
Tel: INT + 44 (0)1 676 52 80 00
Fax: INT + 44 (0)1 676 52 80 01

**AUSTRIA, GERMANY, SWITZERLAND &
EASTERN EUROPE**
Dow Corning GmbH
GERMANY
Tel: INT + 49 (0)611 - 23 71
Fax: INT + 49 (0)611 - 237 610

**ITALY & EASTERN MEDITERRANEAN
COUNTRIES**
Dow Corning S.p.A.
ITALY
Tel: INT + 39 039 - 60 711
Fax: INT + 39 039 - 68 99 660

POLAND
Dow Corning Polska Sp. zo.o.
Tel: INT + 48 (0)22 645 14 45
Fax: INT + 48 (0)22 645 14 40

SPAIN & PORTUGAL
Dow Corning Ibérica S.A.
SPAIN
Tel: INT + 34 (0)93 - 405 12 15
Fax: INT + 34 (0)93 - 405 38 94

FRANCE & NORTH AFRICA
Dow Corning France S.A.
FRANCE
Tel: INT + 33 (0)4 72 84 13 60
Fax: INT + 33 (0)4 72 84 13 79

**R
12/98**